

# STANDARD COLORANT BASE

APROX. TONE	C.I.	COLOUR	REF	LIGHT FASTNESS (ASTM D4303)		THERMAL STABILITY (DIN EN 12877)	MIGRATION (DIN EN 20105-A03)
				Full Shade (1-8)	Tint Shade (1-8)	°C	(1-5)
	P.W.6	WHITE	B.C. WHITE 6	8	8	300	5
	PY53	YELLOW	B.C. YELLOW 53	8	8	300	5
	PY180	YELLOW	B.C. YELLOW 180	6-7	6	290	5
	PY183	YELLOW	B.C. YELLOW 183	7	6	300	5
	PO64	ORANGE	B.C. ORANGE 64	7	6	280	5
	PR254	RED	B.C. RED 254	7	6-7	250	5
	PR122	RED	B.C. RED 122	8	8	300	5
	PR177	RED	B.C. RED 177	8	7	260	5
	PR101	RED	B.C. RED 101/130	8	8	300	5
	PR101	RED	B.C. RED 101/160	8	8	300	5
	PB36	BLUE	B.C. BLUE 36	8	8	300	5
	PB28	BLUE	B.C. BLUE 28	8	8	300	5
	PB29	BLUE	B.C. BLUE 29	8	8	300	5
	PB15:3	BLUE	B.C. BLUE 15:3	8	7-8	300	5
	PB15:1	BLUE	B.C. BLUE 15:1	8	7-8	300	5
	PV19	VIOLET	B.C. VIOLET 19	8	8	300	5
	PV15	VIOLET	B.C. VIOLET 15	7-8	7	270	5
	PG17	GREEN	B.C. GREEN 17	8	8	300	5
	PG7	GREEN	B.C. GREEN 7	8	7-8	280	5
	PBK7	BLACK	B.C. BLACK 7	8	8	300	5
	PBK28	BLACK	B.C. BLACK 28	8	8	300	5

Omega Colors, S.L.

C/Pintor Velázquez, 2-4 Nave 15  
08213 Polinyà (Barcelona) SPAIN

