




















COLORANT BASES FOOD

TONE APROX.	C.I.	COLOUR	UNDERTONE	RAL (aprox.)	REF	LIGHT STABILITY (ASTM D4303)		THERM STABILITY (DIN EN 12877)	MIGRATION (DIN EN 20105-A03)	FOOD CONTACT CERTIFICATIONS			
						TLL.	TR/1:3	SILICONE	SILICONE	Ap 89(1)	French P.L. Circ.176	BfR Rec. IX	FDA 21 CFR 178.3297
													
	P.W.6	WHITE	Bluish	9016	B.C. WHITE 6	8	8	300	5	ok	ok	ok	ok
	PY53	YELLOW	Greenish	1016	B.C. YELLOW 53	8	8	300	5	ok	ok	ok	2% max.
	PY180	YELLOW	Reddish	1018	B.C. YELLOW 180	6-7	6	290	5	ok	ok	ok	5% max.
	PO64	ORANGE	-	2004	B.C. ORANGE 64	7	6	280	5	ok	ok	ok	Nok
	PR243	RED	Yellowish	3020	B.C. RED 243	8	6-7	250	5	ok	ok	ok	5% max.
	PR122	RED	Bluish	3005	B.C. RED 122	8	7	260	5	ok	ok	ok	5% max.
	PR101	RED	-	3013	B.C. RED 101	8	8	300	5	ok	ok	ok	ok
	PB36	BLUE	Greenish	5017	B.C. BLUE 36	8	8	300	5	ok	ok	ok	Nok
	PB29	BLUE	-	5002	B.C. BLUE 29	8	8	300	5	ok	ok	ok	ok
	PB15:1	BLUE	-	5011	B.C. BLUE 15:1	8	7-8	300	5	ok	ok	ok	ok
	PV15	VIOLET	-	5022	B.C. VIOLET 15	7-8	7	270	5	ok	ok	ok	ok
	PG17	GREEN	-	6010	B.C. GREEN 17	8	8	300	5	ok	ok	ok	10% max.
	PG7	GREEN	-	6004	B.C. GREEN 7	8	7-8	280	5	ok	ok	ok	ok
	PBK28	BLACK	Bluish	9004	B.C. BLACK 28	8	8	300	5	ok	ok	ok	5% max.

OMEGA COLORS, S.L.

C/Pintor Velázquez, 2-4 Nave 15
08213 Polinyà (Barcelona)

